

Total Mineral Resource for El Domo

Resource Category	Tonnes (Mt)	Grade					Contained Metal				
		Cu (%)	Pb (%)	Zn (%)	Au (g/t)	Ag (g/t)	Cu (kt)	Pb (kt)	Zn (kt)	Au (koz)	Ag (koz)
Measured	1.4	1.92	0.37	3.52	3.75	58	27.8	5.3	50.9	174	2,704
Indicated	7.5	2.02	0.26	2.81	2.33	49	150.9	19.7	210.3	559	11,884
M+i	8.9	2.00	0.28	2.93	2.56	51	178.7	25.0	261.3	733	14,588
Inferred	1.3	1.52	0.20	2.25	1.83	42	20.1	2.7	29.7	78	1,783

Pit Constrained Mineral Resource for El Domo

Resource Category	Tonnes (Mt)	Grade					Contained Metal				
		Cu (%)	Pb (%)	Zn (%)	Au (g/t)	Ag (g/t)	Cu (kt)	Pb (kt)	Zn (kt)	Au (koz)	Ag (koz)
Measured	1.4	1.92	0.37	3.52	3.75	58	27.8	5.3	50.9	174	2,704
Indicated	5.7	1.74	0.28	2.60	2.47	51	99.0	16.1	147.8	452	9,417
M+i	7.1	1.78	0.30	2.78	2.73	53	126.8	21.4	198.7	627	12,121
Inferred	0.7	0.67	0.21	1.72	1.60	46	4.6	1.5	11.9	36	1,032

Underground Mineral Resource for El Domo

Resource Category	Tonnes (Mt)	Grade					Contained Metal				
		Cu (%)	Pb (%)	Zn (%)	Au (g/t)	Ag (g/t)	Cu (kt)	Pb (kt)	Zn (kt)	Au (koz)	Ag (koz)
Indicated	1.8	2.91	0.20	3.51	1.85	43	51.9	3.6	62.5	106	2,467
Inferred	0.6	2.46	0.19	2.82	2.09	37	15.5	1.2	17.8	42	751

Notes for the above Mineral Resource Tables:

1. Mineral Resources in these tables are effective as of as of May 2, 2019
2. CIM (2014) definitions were followed for Mineral Resources
3. A nominal minimum thickness of two metres was applied to the Mineral Resource wireframes
4. Bulk density assigned on a block per block basis using the correlation between measured density values and base metal grade
5. Mineral Resources are reported above a cut-off net smelter return ("NSR") value of US\$25 per tonne for potential open-pit Mineral Resources and US\$100 per tonne for potential underground Mineral Resources
6. NSR value is based on estimated metallurgical recoveries, assumed metal prices and smelter terms; which include payable factors treatment charges, penalties, and refining charges
7. Metal price assumptions were: US\$3.15/lb Cu, US\$1.00/lb Pb, US\$1.15/lb Zn, US\$1,350/oz Au and US\$18/oz Ag
8. Metallurgical recoveries assumptions were based on three mineral types defined by the metal ratio Cu/(Pb+Zn):
 - Zinc Mineral (Cu/(Pb+Zn)<0.33): 84% Cu, 84% Pb, 95% Zn, 51% Au and 71% Ag
 - Mixed Cu/Zn Mineral (0.33≤Cu/(Pb+Zn)≤3.0): 88% Cu, 85% Pb, 96% Zn, 66% Au and 69% Ag
 - Copper Mineral (Cu/(Pb+Zn)>3.0): 88% Cu, 69% Pb, 73% Zn, 27% Au and 50% Ag
9. NSR factors were also based on the metal ratio Cu/(Zn+Pb):
 - Zinc Mineral (Cu/(Pb+Zn)<0.33): 29.94 US\$/% Cu, 9.17 US\$/% Pb, 11.52 US\$/% Zn, 14.17 US\$/g Au and 0.27 US\$/g Ag
 - Mixed Cu/Zn Mineral (0.33≤Cu/(Pb+Zn)≤3.0): 44.20 US\$/% Cu, 11.34 US\$/% Zn, 22.90 US\$/g Au and 0.27 US\$/g Ag
 - Copper Mineral (Cu/(Pb+Zn)>3.0): 46.27 US\$/% Cu, 6.86 US\$/g Au and 0.19 US\$/g Ag
10. Numbers may not add due to rounding